



Flexiglass[®] 2022

GRP Multi Surface Overlay System



RESIN

CATALYST

	Cool 5-9°C	Moderate 10-17°C	Hot 18-30 °C
1L 1.46kg	100g	50g	25g
2L 2.9kg	150g	100g	50g
3L 4.4kg	250g	150g	100g
4L 5.8kg	300g	200g	100g
5L 7.3kg	400g	250g	150g
6L 8.8kg	450g	300g	150g
7L 10.2kg	550g	350g	200g
8L 11.7kg	600g	400g	200g
9L 13.1kg	700g	450g	250g
10L 14.6kg	750g	500g	300g

PRIMER

CATALYST



	Cool 5-9°C	Moderate 10-17°C	Hot 18-30 °C
1L 1.2kg	100g	50g	25g
2L 2.4kg	150g	100g	50g
3L 3.6kg	200g	150g	100g
4L 4.8kg	250g	200g	100g
5L 6kg	300g	200g	150g

Mixing Bucket

Mixing Bucket

Usage Guide

AREA	Approx. Coverage: 500g per m ² 350ml per m ²		Based on temp: 10°C-17°C			Approx. Coverage: 1.7kg per m ² 1.2L per m ²		Based on temp: 10°C-17°C			Approx. Coverage: 225gsm 33kg 146m ² 225gsm 16.5kg 73m ² 225gsm 6.75kg 30m ²					
	PRIMER	5kg TIN	CATALYST for PRIMER	50g	100g	200g	RESIN	20kg TIN	CATALYST for RESIN	50g	100g	200g	MATTING 225gsm	6.75kg	16.5kg	33kg
5m ²	2.5kg	1	100g	0	1	0	8.5kg	1	300g	0	1	1	1	0	0	0
10m ²	5kg	1	200g	0	0	1	17kg	1	600g	0	0	3	1	0	0	0
15m ²	7.5kg	2	300g	0	1	1	25.5kg	2	900g	0	1	4	1	0	0	0
20m ²	10kg	2	400g	0	0	2	34kg	2	1.2kg	0	0	6	1	0	0	0
25m ²	12.5kg	3	450g	1	0	2	42.5kg	3	1.6kg	0	0	8	1	0	0	0
30m ²	15kg	3	500g	0	1	2	51kg	3	1.75kg	1	1	8	1	0	0	0
35m ²	17.5kg	4	600g	0	0	3	59.5kg	3	2.1kg	0	1	10	0	1	0	0
40m ²	20kg	4	800g	0	0	4	68kg	4	2.4kg	0	0	12	0	1	0	0
50m ²	25kg	5	1kg	0	0	5	85kg	5	2.8kg	0	0	14	0	1	0	0
60m ²	30kg	6	1.2kg	0	0	6	102kg	6	3.5kg	0	1	17	0	1	0	0
70m ²	35kg	7	1.4kg	0	0	7	119kg	6	4.2kg	0	0	21	0	1	0	0
80m ²	40kg	8	1.6kg	0	0	8	136kg	7	4.55kg	1	1	22	0	0	1	1
90m ²	45kg	9	1.8kg	0	0	9	153kg	8	5.25kg	1	0	26	0	0	1	1
100m ²	50kg	10	2kg	0	0	10	170kg	9	5.95kg	1	1	29	0	0	1	1



For more information please visit:
cromarbuildingproducts.com/acrypol-flexiglass/
 Or scan the code.



Fill in our online form to start your training journey.

